

Pinja Flex Combi 35

Beskrivelse

A one-component water-borne polyacrylate paint with excellent adhesion properties.

Produktegenskaber og anbefalet brug

- A fast-drying exterior paint for windows and doors. It forms an elastic film with low water permeability properties. These attributes help the product protect wood against moisture and dirt
- Excellent adhesion to bare wood. The possibility to use the product both as a primer and a topcoat results in more efficient production. Good hiding power and filling properties ensure the high quality of the dry paint film
- Beautifies wooden windows and front doors with thousands of durable colors
- Suitable for wooden window frames and front doors

TEKNISK DATA

Volumen tørstof

38% (A base)
33% (C base)

Vægt tørstof

49% (A base)
40% (C base)

Massefylde

1.20 kg/l (A base)
1.12 kg/l (C base)

Anbefalet påføringsmængde og teoretisk dækkeevne

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Tørretid

Stacking temperature below +30°C.

Drying and recoating times are related to the colour shade, film thickness, temperature, the relative humidity of the air and ventilation.

Glans

Halvmat.

Farver

The shades on the Wooden Facades colour card for exterior use. RAL and NCS color cards. Avatint tinting system.

Pinja Flex Combi 35

PÅFØRINGSINSTRUKSER

Forbehandling	Clean surfaces from dirt, dust and loose material. Assure that surface is free from mould and blue stain. Wood surfaces must be sanded with sandpaper P150–320. Sanding prior to the next application with sandpaper P240–400. All sanding dust must be removed.
Anbefalede primere	Pinjadur Primer, Pinja Flex Combi 35, Pinja Flex Isolator, Pinja Flex Primer, Pinja Wood Stain, Pinja Indeeep.
Påføringsforhold	The surface to be treated has to be clean and dry. The moisture content of wood has to be below 20%. During application and drying temperature of the air, substrate and paint must be over +18°C and relative humidity of the air below 70%. Good ventilation is required to ensure optimal result. Product can be dried with or without oven.
Påføring	Stir the product carefully before use. Avoid floatation. For airless spraying recommended nozzle tip is 0.011"–0.015" and pressure 80–160 bar. Spray angle shall be chosen according to the shape of the object. For air-assisted airless spraying recommended nozzle tip is 0.011"–0.015" and pressure 40–120 bar. Spray angle shall be chosen according to the shape of the object. Wood contains resin and other colouring extractives especially in knots. Temperature and humidity fluctuations may cause paint coat discolouration in these areas.
Rengøring af udstyr	Water or Tikkurila Tool Cleaner.
VOC	According to VOC Directive 2004/42/EU the product subcategory A/d VOC limit (1.1.2010) is maximum 130 g/l. VOC content of the "Pinja Flex Combi 35" is 20±10 g/l.
HELBRED OG SIKKERHED	Emballagen er udstyret med sikkerhedsmærkater, som skal bemærkes. Yderligere information om farlige bestanddele og beskyttelse er nærmere beskrevet i individuelle helbreds- og sikkerhedsblade. Helbreds- og sikkerhedsdatablad kan fås ved henvendelse til Tikkurila.

Kun til industriel brug.

Emballagen er udstyret med sikkerhedsmærkater, som skal bemærkes. Yderligere information om farlige bestanddele og beskyttelse er nærmere beskrevet i individuelle helbreds- og sikkerhedsblade. Helbreds- og sikkerhedsdatablad kan fås ved henvendelse til Tikkurila.

Informationen i dette dokument er ikke beregnet på at være udtømmende eller fuldstændigt. Informationen baserer sig på laboratorietests og praktisk erfaring, og er givet efter vores bedste kundskaber. Produkternes kvalitet kontrolleres af vores virksomhedssystem, baseret på krav om ISO 9001 og ISO 14001. Som producent kan vi ikke kontrollere de omstændigheder, under hvilke produkterne anvendes eller de mange faktorer som påvirker brugen og påføring af produkterne. Tikkurila er ikke ansvarlig for tilfælde hvor produkterne anvendes i strid med anvisningerne eller for uanvendelige objekter. Vi forbeholder os retten at ændre den givne information uden varsel.