

# Temacoat SPA 50

**Beskrivelse** A two-component resin modified epoxy paint.

**Produktegenskaber og anbefalet brug**

- Can be applied to steel, zinc and aluminium. Rapidly recoatable and ready to handle paint. It is also suitable as a single-coat system
- Forms durable film with good mechanical, chemical and climatic resistant properties. Excellent as a primer, intermediate or finish coat on surfaces exposed to stress
- Recommended for building frameworks, tubular bridges, conveyors and other steelwork and equipment

## TEKNISK DATA

**Volumen tørstof** 68±2% (ISO 3233)

**Vægt tørstof** 81±2%

**Massefylde** 1.4–1.5 kg / l (mixed)

**Blandingsforhold** Base 4 parts by volume Temacoat SPA 50  
Hardener 1 part by volume 008 5607

**Pot life(+23°C)** 6 hours

**Anbefalet lagtykkelse og teoretisk dækkeevne**

Recommended film thicknesses		Theoretical coverage
wet	dry	
115µm	80µm	8.5 m <sup>2</sup> /l
215µm	150µm	4.5 m <sup>2</sup> /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

**Tørretid**

DFT 100 µm	0°C	+10°C	+23°C	+35°C
Dust dry, after	16h	4h	2h	1h
Touch dry, after	24h	10h	4h	2h
Recoatable, min. after	24h	3h	1h	½h
Recoatable, surfaces to be submerged, min. after	4d	28h	12h	6h
Recoatable with polyurethane paints, min. after	1d	5h	2h	1h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

**Glans** Halvblank.

**Farvenuancer** RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards. Temaspeed Premium tinting

# Temacoat SPA 50

## PÅFØRINGSINSTRUKSER

<b>Overflade forberedelse</b>	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p>Zinc surfaces: Sweep blast clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Panssaripesu detergent. For hot dip galvanized surfaces see separate application instructions or contact Tikkurila Technical Service.</p> <p>Aluminium surfaces: Sweep blast clean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Maalipesu detergent.</p> <p>Primed surfaces: Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)</p>
<b>Anbefalede primere</b>	Temacoat SPA Primer, Temazinc 77, Temazinc 99.
<b>Anbefalede topcoats</b>	Temacoat HB 30, Temacoat GPL, Temacoat GS 50, Temacoat GPL-S MIO, Temacoat SPA 50, Temadur 10, Temadur 20, Temadur 50, Temadur 90, Temadur HB 50, Temadur HB 80, Temadur HS 90, Temadur SC 20, Temadur SC 50, Temadur SC 80, Temadur SC-F 20, Temadur SC-F 50, Temadur SC-F 80, Temathane 50, Temathane 90, Temathane PC 50, Temathane PC 80.
<b>Påføringsforhold</b>	<p>All surfaces must be clean, dry and free from contamination. During application and drying the temperature of the surface should not fall below 0°C. The surface temperature of steel should remain at least 3°C above the dew point. Relative humidity of the air should not exceed 80% during application and drying.</p> <p>The product should not be applied at temperatures below 0°C when there is a possibility of ice formation on the substrate. For proper application the temperature of the product itself should be above +15°C during mixing and application. Good ventilation and sufficient air movement is required in confined areas during application and drying.</p> <p>Note! There is a natural tendency of this coating to chalk, discolor or yellow unevenly. It is recommended to use polyurethane topcoat when there are high aesthetical requirements on color appearance.</p>
<b>Blanding af komponenter</b>	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use power mixer for mixing. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface and weaken the properties of the coating.
<b>påføring</b>	<p>For airless spraying, the product is thinned approximately 0–10%. Recommended nozzle tip is 0.015"–0.021" and pressure 120–180 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For brush application product should be thinned according to the circumstances.</p>
<b>Fortyndere</b>	Thinner 1031
<b>Rengøring af udstyr</b>	Thinner 1031.



## Temacoat SPA 50

<b>VOC</b>	The Volatile Organic Compounds amount is 300 g/litre of paint mixture.  VOC content of the paint mixture (thinned 10% by volume) is 360 g/l.
<b>HELBRED OG SIKKERHED</b>	Emballagen er udstyret med sikkerhedsmærkater, som skal bemærkes. Yderligere information om farlige bestanddele og beskyttelse er nærmere beskrevet i individuelle helbreds- og sikkerhedsblade. Helbreds- og sikkerhedsdatablad kan fås ved henvendelse til Tikkurila.

Emballagen er udstyret med sikkerhedsmærkater, som skal bemærkes. Yderligere information om farlige bestanddele og beskyttelse er nærmere beskrevet i individuelle helbreds- og sikkerhedsblade. Helbreds- og sikkerhedsdatablad kan fås ved henvendelse til Tikkurila.

Informationen i dette dokument er ikke beregnet på at være udtømmende eller fuldstændigt. Informationen baserer sig på laboratorietests og praktisk erfaring, og er givet efter vores bedste kundskaber. Produkternes kvalitet kontrolleres af vores virksomhedssystem, baseret på krav om ISO 9001 og ISO 14001. Som producent kan vi ikke kontrollere de omstændigheder, under hvilke produkterne anvendes eller de mange faktorer som påvirker brugen og påføring af produkterne. Tikkurila er ikke ansvarlig for tilfælde hvor produkterne anvendes i strid med anvisningerne eller for uanvendelige objekter. Vi forbeholder os retten at ændre den givne information uden varsel.