

Temafloor AC502

Beskrivelse

A two-component, solvent-free, elastic acrylic binder.

Produktegenskaber og anbefalet brug

- Used as a binder for Temafloor AC acrylic troweling screed
- Suitable to be used as a self-levelling coating and as a binder of a coloured sand screed
- Suitable also for indoor asphalt floors
- Mixed with sand also suitable for patching of concrete floors
- Cures fast also in low temperatures
- Recommended for the floors of engineering workshops, warehouses, cold stores of food industry parking deck surfaces, loading ramps and terraces

TEKNISK DATA

Volumen tørstof

approx. 100%

Massefylde

0.98 kg /l (ready made mixture)

Blandingsforhold

Self-levelling screeds 5–6 mm:
Temafloor AC502 30 w-%
Coloured sand Ø 0,1–0,6 mm 30 w-%
Coloured sand Ø 0,3–0,8 mm 40 w-%
Surface is fully broadcast with coloured sand Ø 0.6–1.2 mm.

Mulige hædere

BP-50-FT, Perkadox®CH-50 or PEROXAN BP-Pulver 50 W.

Dækkeevne

For a flat substrate:
2 mm layer: 2 litres ready for use screed / m²
6 mm layer: 6 litres ready for use screed / m²
Practical coverage depends on the evenness of the substrate.

Rengøring af udstyr

Thinner 006 1400.

Glans

Halvmat.

Farver

The colour of the screed is determined by the sand used.

Fortyndingsinstruktioner

Do not thin.

VOC

VOC 2004/42/EC (cat A/j), 500 g/l (2010)
Temafloor AC502: max. VOC < 500 g/l.

Emballagestørrelser

200,0 L

Temafloor AC502

PÅFØRINGSINSTRUKSER

Overflade forberedelse New concrete: Remove laitance by power grinding, vacuum grit blasting or hydrochloric acid etching. Choose the method best suited for the premises. After grinding remove dust carefully with a vacuum cleaner. Hydrochloric acid etching is carried out with diluted hydrochloric acid (1 part concentrated hydrochloric acid, 4 parts water). Rinse with plenty of water. Dry the floor.

Old concrete: Remove all grease, oil, chemicals and other impurities by Maalipesu detergent. Remove old peeling paint layer by grinding, milling or vacuum grit blasting. Choose the method best suited for the premises. Clean out pot-holes removing all loose friable material. Open cracks with e.g. an abrasive tool. Remove loose material and dust.

Påføringsforhold The relative humidity of the concrete should not exceed 97%. The temperature of the ambient air, surface or coating should not fall below +5°C during application or drying. Relative humidity of air should not exceed 80%.

Blanding af komponenter First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 2 minutes to get homogenous mixture) by using a low speed industrial hand drill with a paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.

Priming Prime using Temafloor AC102 Primer. Pour the primer mixture onto the floor and apply by the trowel or roller as much as is needed to impregnate the concrete surface. If necessary, repeat priming to get a non-porous surface. A porous priming coat will result in holes and air bubbles in the finished coating. Subsequent treatment can be carried out after 30 min.

Scatter sand of grain size Ø 0,4–0,8 mm on the fresh primer coat to ensure the screed adhesion and prohibit gliding of the screed.

Lapning Patch pot-holes and cracks with a mixture of unthinned Temafloor AC502 and dry, clean sand. Mixing ratio e.g. 1 part by volume of varnish mixture and 1–2 parts by volume of sand of grain size 0.1–0.6 mm. Sand the patched areas before overcoating, if necessary.

The floor can be levelled by using Temafloor AC502 and sand of grain size 0,5–1,2 mm.

Note! Concrete surface should always be primed before patching.

Belægning Pour the Temafloor AC502 mixture onto the floor. Apply by an adjustable trowel to the desired thickness. Trowel the screeded surface by hands or use broadcasting technique.

Topcoating Topcoating can be carried out after the screed has cured. Topcoating can be carried out with Temafloor AC602 Clear topcoat. Pour the varnish mixture onto the floor, apply with a rubber trowel and level with a roller.

Note! Add the remaining mixture to the next batch of the product, do not scrape it out of the container onto the floor.

HELBRED OG SIKKERHED

Emballagen er udstyret med sikkerhedsmærkater, som skal bemærkes. Yderligere information om farlige bestanddele og beskyttelse er nærmere beskrevet i individuelle helbreds- og sikkerhedsblade. Helbreds- og sikkerhedsdatablad kan fås ved henvendelse til Tikkurila.

Emballagen er udstyret med sikkerhedsmærkater, som skal bemærkes. Yderligere information om farlige bestanddele og beskyttelse er nærmere beskrevet i individuelle helbreds- og sikkerhedsblade. Helbreds- og sikkerhedsdatablad kan fås ved henvendelse til Tikkurila.

Informationen i dette dokument er ikke beregnet på at være udtømmende eller fuldstændigt. Informationen baserer sig på laboratorietests og praktisk erfaring, og er givet efter vores bedste kundskaber. Produkternes kvalitet kontrolleres af vores virksomhedssystem, baseret på krav om ISO 9001 og ISO 14001. Som producent kan vi ikke kontrollere de omstændigheder, under hvilke produkterne anvendes eller de mange faktorer som påvirker brugen og påføring af produkterne. Tikkurila er ikke ansvarlig for tilfælde hvor produkterne anvendes i strid med anvisningerne eller for uanvendelige objekter. Vi forbeholder os retten at ændre den givne information uden varsel.

Temafloor AC502

EN 13813

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA	
13	
TIK-1600-5003b	
EN 13813 SR-B2,0-AR 0,5-IR 4	
slagfasthed	IR4
frigivelse af ætsende stoffer	SR

EN 1504-2:2004

	
0809	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
0809-CPD-0773	
TIK-1600-5003a	
EN 1504-2:2004	
CO2 permabilitet	sd > 50 m
slagfasthed	